



Coating name	Suggested area of use	Finish characteristics	Recommended Reducer	Recommended Sealer	Dry to Touch (approx.)	Re-coat interval	Recommended no. of coats (after sealer applied)	Dry to rub (normal drying conditions)	Colour	Catalyst	Catalyzed pot-life	Recommended stain products		Compatible additives	Available sheens - degree of gloss 60° meter	Sizes stocked
Stringed Instrument Lacquer B611-1406 B611-1407	Specially formulated for use on all types of musical instruments especially acoustic.	Allows for special expansion and contraction that occurs on stringed instruments Easy to apply Excellent rubbing qualities Easy touch-up Fast drying Excellent appearance Highest quality nitrocellulose finish	Qualalacq Thinner B611-0631 Retarder B610-0133	<b>,</b>	4 to 5 minutes	1 hour	Vinyl Sealer If sanding and	24 hour minimum; one week is better	Very pale light yellow	N/A	N/A	Stain B503- Wood Stain	Master Color B500- Solar-Lux Stain B503-	Flattener B610-01006 Fisheye Flow Out B617-0001 Retarder B610-0133	Gloss	945ml 3.7 litre
Stringed Instrument Lacquer Aerosol B104-1406	Specially formulated Aerosol for use on all types of musical instruments especially acoustic.	Allows for special expansion and contraction that occurs on stringed instruments Easy to apply Excellent rubbing qualities Easy touch-up Fast drying Excellent appearance Highest quality nitrocellulose finish	N/A	Vinyl Sealer Aerosol B102-8000 (must be used to achieve required finish properties).	7 to 8 minutes	of 4 coats	2 coats of Vinyl Sealer Aerosol and 4 coats of Stringed Instument Lacquer. If sanding and rubbing to a high gloss, use 8 to 10 coats depending on the porosity of the wood.	one week is	Very pale light yellow	N/A	N/A	Guitar Toner Aerosols B104-1201/2 (especially good for applying sunburst effect) Wiping Stain Aerosols B115-08	N/A	N/A	Gloss	369g
Violin Varnish B603-09055	Specially formulated for use on all types of musical instruments.	Blend of shellac flakes, gum mastic and gum sandarac. Produces a tough, hard, elastic, water resistant film. Easy to apply Excellent rubbing qualities Easy touch-up Fast drying Excellent appearance	Bekhol Propriety Solvent B603-2816	n/a	4 hours	12 hours	1 coat, sand, then 2 coats, only lightly scuff sanding between coats	12 hours	Pale amber	N/A	N/A	Solar-Lux Stain B503- Wood Stain B545-	N/A	N/A	Gloss	473ml

Always read safety sheets. Always test products on a hidden area.

© 2008 Behlen Ltd.